



Natural stone – Water absorption

REPORT Nº: **232936PN003**

DATE: **23-02-2023**

PAGE: **1/2**

PETITIONER: **LT Granit Oy**
Koskentie 4, FI-54410 Ylämaa. (Finland)

SAMPLE IDENTIFICATION:

Date of delivery **03-01-2023**
Description **6 cubic specimens of nominal dimensions 50x50x50 mm**
Commercial name * **Baltic Brown**
Petrographic definition * **–**
Place of quarrying * **Helppäantie 422, FI-54410 Ylämaa, Finland**
Coordinates * **N: 60.833003, E: 27.846321**
Supplier * **LT Granit Oy**
Sampled by * **Jarmo Tielinen (05-10-2022)**

* Information declared by the petitioner

TEST METHOD: **EN 13755:2008 Natural stone test methods. Determination of water absorption at atmospheric pressure**
Deviations **–**
Specimen preparation **–**
Place of testing **Centro Tecnológico del Mármol**
Dates of testing **25-01-2023 / 03-02-2023**





TEST REPORT

Natural stone – Water absorption

REPORT Nº: **232936PN003**

DATE: **23-02-2023**

PAGE: **2/2**

RESULTS:

Specimen

Water absorption, A_b (%)

Mean value of water absorption, \bar{A}_b

01	02	03	04	05	06
0,1	0,1	0,1	0,1	0,1	0,1
0,1 %					

Remarks: The uncertainties are calculated and at the client's disposal
The results are expressed to the nearest 0,1 %

DISCLAIMER:

The laboratory is not responsible for the sampling or for the information declared by the client. The results refer only to the sample received at the laboratory, on the expressed date.
This report shall not be reproduced, except in full, without the written consent of the laboratory.

Digitally signed by

Antonio Molina
Director Técnico



Natural stone – Apparent density and open porosity

REPORT Nº: **232936PN004A** DATE: **23-02-2023**

PAGE: **1/2**

PETITIONER: **LT Granit Oy**
Koskentie 4, FI-54410 Ylämaa. (Finland)

SAMPLE IDENTIFICATION:

Date of delivery **03-01-2023**
Description **6 cubic specimens of nominal dimensions 50x50x50 mm**
Commercial name * **Baltic Brown**
Petrographic definition * **–**
Place of quarrying * **Helppääntie 422, FI-54410 Ylämaa, Finland**
Coordinates * **N: 60.833003, E: 27.846321**
Supplier * **LT Granit Oy**
Sampled by * **Jarmo Tielinen (05-10-2022)**

* Information declared by the petitioner

TEST METHOD: **EN 1936:2007 Natural stone test methods. Determination of real density and apparent density, and of total and open porosity. Section 8.1**

Deviations **–**
Specimen preparation **–**
Place of testing **Centro Tecnológico del Mármol**
Dates of testing **18-01-2023 / 24-01-2023**





TEST REPORT

Natural stone – Apparent density and open porosity

REPORT Nº: **232936PN004A** DATE: **23-02-2023**

PAGE: **2/2**

RESULTS:

Specimen	07	08	09	10	11	12
Apparent density, ρ_b (kg/m ³)	2660	2660	2680	2690	2660	2680
Open porosity, p_o (%)	0,3	0,3	0,3	0,3	0,3	0,4
Mean value of apparent density, $\bar{\rho}_b$	2670 kg/m ³					
Mean value of open porosity, \bar{p}_o	0,3 %					

Remarks: The uncertainties are calculated and at the client's disposal
The results of density are expressed to the nearest 10 kg/m³
The results of porosity are expressed to the nearest 0,1 %

DISCLAIMER:

The laboratory is not responsible for the sampling or for the information declared by the client. The results refer only to the sample received at the laboratory, on the expressed date.
This report shall not be reproduced, except in full, without the written consent of the laboratory.

Digitally signed by

Antonio Molina
Director Técnico



Natural stone – Abrasion resistance (Capon method)

REPORT Nº: **232936PN006**

DATE: **23-02-2023**

PAGE: **1/2**

PETITIONER: **LT Granit Oy**
Koskentie 4, FI-54410 Ylämaa. (Finland)

SAMPLE IDENTIFICATION:

Date of delivery **03-01-2023**
Description **6 polished slabs of 150x150x30 mm**
Commercial name * **Baltic Brown**
Petrographic definition * **–**
Place of quarrying * **Helppääntie 422, FI-54410 Ylämaa, Finland**
Supplier * **N: 60.833003, E: 27.846321**
Sampled by * **LT Granit Oy**
Planes of anisotropy * **Jarmo Tielinen (05-10-2022)**

* Information declared by the petitioner

TEST METHOD: **EN 14157:2017 Natural stone test methods. Determination of the abrasion resistance. Section 3**

Deviations **–**
Specimen preparation **–**
Calibration factor **0,3 mm**
Place of testing **Centro Tecnológico del Mármol**
Dates of testing **01-02-2023 / 06-02-2023**





TEST REPORT

Natural stone – Abrasion resistance (Capon method)

REPORT Nº: **232936PN006**

DATE: **23-02-2023**

PAGE: **2/2**

RESULTS:

Specimen	13	14	15	16	17	18
Groove lengths (mm)	13,0	13,0	13,0	13,5	12,5	13,0
	14,5	15,0	14,0	14,0	14,0	12,5
Mean value of groove length	14,0 mm					
Standard deviation	0,6 mm					
Higher expected value, E_H	15,5 mm					

Remarks: The uncertainties are calculated and at the client's disposal
The results are expressed to the nearest 0,5 mm
According to EN 14157, only the biggest grooves of each specimen are considered

DISCLAIMER:

The laboratory is not responsible for the sampling or for the information declared by the client. The results refer only to the sample received at the laboratory, on the expressed date.
This report shall not be reproduced, except in full, without the written consent of the laboratory.

Digitally signed by

Antonio Molina
Director Técnico



Natural stone – Frost resistance (technological test)

REPORT Nº: **232936PN008B** DATE: **23-02-2023**

PAGE: **1/4**

PETITIONER: **LT Granit Oy**
Koskentie 4, FI-54410 Ylämaa. (Finland)


SAMPLE IDENTIFICATION:

Date of delivery **03-01-2023**
Description **2 sets of 10 specimens of nominal dimensions 300x50x50 mm**
Commercial name * **Baltic Brown**
Petrographic definition * **–**
Place of quarrying * **Helppääntie 422, FI-54410 Ylämaa, Finland**
Coordinates * **N: 60.833003, E: 27.846321**
Supplier * **LT Granit Oy**
Sampled by * **Jarmo Tielinen (05-10-2022)**
Planes of anisotropy * **–**

* Information declared by the petitioner

TEST METHOD: **EN 12371:2010 Natural stone test methods. Determination of frost resistance. Section 7.3.1**

Deviations **–**
Specimen preparation **–**
Conditioning **Drying in oven at 70±5°C to constant mass**
Load direction **–**
Place of testing **Centro Tecnológico del Mármol**
Dates of testing **11-01-2023 / 15-02-2023**



Natural stone – Frost resistance (technological test)

REPORT Nº: **232936PN008B** DATE: **23-02-2023**

PAGE: **2/4**

RESULTS:

Set 1 (not subjected to freeze-thaw cycles)

Specimen	49	50	51	52	53	54	55	56	57	58
Breaking thickness, h (mm)	50,2	49,7	49,8	50,2	49,7	50,1	50,3	50,1	50,2	49,8
Breaking width, b (mm)	50,5	50,2	50,5	49,8	50,4	50,3	49,8	50,3	50,1	50,2
Span, l (mm)	250,0	250,0	250,0	250,0	250,0	250,0	250,0	250,0	250,0	250,0
Load increase (MPa/s)	0,25	0,25	0,25	0,25	0,25	0,25	0,25	0,25	0,25	0,25
Breaking load, F (N)	4380	3890	5010	4920	4220	3720	4170	4300	4640	4380
Distance fracture to centre (mm)	14,1	2,4	8,0	4,9	5,2	10,0	14,4	3,4	13,3	19,4
Flexural strength, R_{tf} (MPa)	12,9	11,7	15,0	14,7	12,7	11,0	12,4	12,8	13,8	13,2

Set 2 (subjected to 56 freeze-thaw cycles)

Specimen	19	20	21	22	23	24	25	26	27	28
Breaking thickness, h (mm)	50,2	50,1	49,9	50,6	50,8	49,9	50,5	50,5	50,2	50,4
Breaking width, b (mm)	49,3	50,2	50,3	49,8	49,5	50,0	49,6	49,6	49,8	50,6
Span, l (mm)	250,0	250,0	250,0	250,0	250,0	250,0	250,0	250,0	250,0	250,0
Load increase (MPa/s)	0,25	0,25	0,25	0,24	0,25	0,25	0,25	0,25	0,25	0,24
Breaking load, F (N)	3680	3890	3840	4810	4040	4010	3710	3340	4380	3970
Distance fracture to centre (mm)	23,9	7,8	8,0	2,2	10,7	6,8	10,6	11,6	1,1	11,3
Flexural strength, R_{tf} (MPa)	11,1	11,6	11,5	14,1	11,9	12,1	11,0	9,9	13,1	11,6



TEST REPORT

Natural stone – Frost resistance (technological test)

REPORT Nº: **232936PN008B** DATE: **23-02-2023**

PAGE: **3/4**

Mean value of flexural strength, F_0

13,0 MPa

Standard deviation, s

1,2 MPa

Mean value of flexural strength after 56 cycles, F_{56}

11,8 MPa

Standard deviation, s

1,2 MPa

Decrease of flexural strength after 56 cycles

9,0 %

Remarks: The uncertainties are calculated and at the client's disposal

The sample received consisted of 20 undifferentiated specimens. The separation between the two sets of 10 specimens to be tested, was carried out at random by the laboratory

DISCLAIMER:

The laboratory is not responsible for the sampling or for the information declared by the client. The results refer only to the sample received at the laboratory, on the expressed date.

This report shall not be reproduced, except in full, without the written consent of the laboratory.

Digitally signed by

Antonio Molina
Director Técnico

Natural stone – Frost resistance (technological test)

REPORT Nº: 232936PN008B DATE: 23-02-2023

PAGE: 4/4

Set 2 before freeze-thaw cycles



Set 2 after 56 freeze-thaw cycles





Natural stone – Frost resistance (technological test)

REPORT Nº: **232936PN008D** DATE: **23-02-2023**

PAGE: **1/4**

PETITIONER: **LT Granit Oy**
Koskentie 4, FI-54410 Ylämaa. (Finland)

SAMPLE IDENTIFICATION:

Date of delivery **03-01-2023**
Description **2 sets of 10 cubic specimens of nominal dimensions 70x70x70 mm**
Commercial name * **Baltic Brown**
Petrographic definition * **–**
Place of quarrying * **Helppääntie 422, FI-54410 Ylämaa, Finland**
Coordinates * **N: 60.833003, E: 27.846321**
Supplier * **LT Granit Oy**
Sampled by * **Jarmo Tielinen (05-10-2022)**
Planes of anisotropy * **–**

* Information declared by the petitioner

TEST METHOD: **EN 12371:2010 Natural stone test methods. Determination of frost resistance. Section 7.3.1**

Deviations **–**
Specimen preparation **–**
Conditioning **Drying in oven at 70±5°C to constant mass**
Load direction **–**
Place of testing **Centro Tecnológico del Mármol**
Dates of testing **11-01-2023 / 15-02-2023**



TEST REPORT

Natural stone – Frost resistance (technological test)

REPORT Nº: **232936PN008D** DATE: **23-02-2023**

PAGE: **2/4**

RESULTS:

Set 1 (not subjected to freeze-thaw cycles)

Specimen	39	40	41	42	43	44	45	46	47	48
Average width of faces, \bar{l} (mm)	70,5	70,5	70,4	70,7	71,0	70,5	70,9	70,4	70,7	70,3
Height, h (mm)	69,4	69,9	69,5	69,6	68,3	70,2	69,8	69,8	69,5	70,0
Breaking load, F (kN)	890	760	970	870	890	750	970	930	830	840
Compressive strength, R (MPa)	179	153	196	175	177	151	192	189	167	170

Set 2 (subjected to 56 freeze-thaw cycles)

Specimen	29	30	31	32	33	34	35	36	37	38
Average width of faces, \bar{l} (mm)	70,8	70,7	70,5	70,2	70,0	70,8	70,7	70,2	70,3	70,6
Height, h (mm)	70,0	69,4	70,0	70,1	69,5	70,3	70,3	70,0	69,5	69,7
Breaking load, F (kN)	910	900	730	900	890	780	870	770	910	870
Compressive strength, R (MPa)	182	180	147	183	182	156	174	157	184	175



TEST REPORT

Natural stone – Frost resistance (technological test)

REPORT Nº: **232936PN008D** DATE: **23-02-2023**

PAGE: **3/4**

Mean value of compressive strength, R_0

175 MPa

Standard deviation, s

15 MPa

Mean value of compressive strength after 56 cycles, R_{56}

172 MPa

Standard deviation, s

13 MPa

Decrease of compressive strength after 56 cycles

2,0 %

Remarks: The uncertainties are calculated and at the client's disposal

The sample received consisted of 20 undifferentiated specimens. The separation between the two sets of 10 specimens to be tested, was carried out at random by the laboratory

DISCLAIMER:

The laboratory is not responsible for the sampling or for the information declared by the client. The results refer only to the sample received at the laboratory, on the expressed date.

This report shall not be reproduced, except in full, without the written consent of the laboratory.

Digitally signed by

Antonio Molina
Director Técnico

Natural stone – Frost resistance (technological test)

REPORT Nº: 232936PN008D DATE: 23-02-2023

PAGE: 4/4

Set 2 before freeze-thaw cycles



Set 2 after 56 freeze-thaw cycles



Natural stone – Compressive strength

REPORT Nº: **232936PN009A** DATE: **23-02-2023**

PAGE: **1/2**

PETITIONER: **LT Granit Oy**
Koskentie 4, FI-54410 Ylämaa. (Finland)


SAMPLE IDENTIFICATION:

Date of delivery **03-01-2023**
Description **10 cubic specimens of nominal dimensions 70x70x70 mm**
Commercial name * **Baltic Brown**
Petrographic definition * **–**
Place of quarrying * **Helppääntie 422, FI-54410 Ylämaa, Finland**
Coordinates * **N: 60.833003, E: 27.846321**
Supplier * **LT Granit Oy**
Sampled by * **Jarmo Tielinen (05-10-2022)**
Planes of anisotropy * **–**

* Information declared by the petitioner

TEST METHOD: **EN 1926:2006 Natural stone test methods. Determination of uniaxial compressive strength**

Deviations **–**
Specimen preparation **–**
Conditioning **Drying in oven at 70±5°C to constant mass**
Load direction **–**
Place of testing **Centro Tecnológico del Mármol**
Dates of testing **08-02-2023 / 10-02-2023**





TEST REPORT

Natural stone – Compressive strength

REPORT Nº: **232936PN009A** DATE: **23-02-2023**

PAGE: **2/2**

RESULTS:

Specimen	39	40	41	42	43	44	45	46	47	48
Average width of faces, \bar{l} (mm)	70,5	70,5	70,4	70,7	71,0	70,5	70,9	70,4	70,7	70,3
Height, h (mm)	69,4	69,9	69,5	69,6	68,3	70,2	69,8	69,8	69,5	70,0
Breaking load, F (kN)	890	760	970	870	890	750	970	930	830	840
Compressive strength, R (MPa)	179	153	196	175	177	151	192	189	167	170
Average compressive strength, \bar{R}	175 MPa									
Standard deviation, s	15 MPa									
Coefficient of variation, v	0,09									
Lower expected value, E	145 MPa									

Remarks: The uncertainties are calculated and at the client's disposal

DISCLAIMER:

The laboratory is not responsible for the sampling or for the information declared by the client. The results refer only to the sample received at the laboratory, on the expressed date.

This report shall not be reproduced, except in full, without the written consent of the laboratory.

Digitally signed by

Antonio Molina
Director Técnico



TEST REPORT

Natural stone – Flexural strength

REPORT Nº: **232936PN010** DATE: **23-02-2023** PAGE: **1/2**

PETITIONER: **LT Granit Oy**
Koskentie 4, FI-54410 Ylämaa. (Finland)

SAMPLE IDENTIFICATION:

Date of delivery **03-01-2023**
Description **10 specimens of nominal dimensions 300x50x50 mm**
Commercial name * **Baltic Brown**
Petrographic definition * **–**
Place of quarrying * **Helppääntie 422, FI-54410 Ylämaa, Finland**
Coordinates * **N: 60.833003, E: 27.846321**
Supplier * **LT Granit Oy**
Sampled by * **Jarmo Tielinen (05-10-2022)**
Planes of anisotropy * **–**

* Information declared by the petitioner

TEST METHOD: **EN 12372:2006 Natural stone test methods. Determination of flexural strength under concentrated load**

Deviations **–**
Specimen preparation **–**
Conditioning **Drying in oven at 70±5°C to constant mass**
Load direction **–**
Place of testing **Centro Tecnológico del Mármol**
Dates of testing **08-02-2023 / 14-02-2023**





TEST REPORT

Natural stone – Flexural strength

REPORT Nº: **232936PN010**

DATE: **23-02-2023**

PAGE: **2/2**

RESULTS:

Specimen	49	50	51	52	53	54	55	56	57	58
Breaking thickness, h (mm)	50,2	49,7	49,8	50,2	49,7	50,1	50,3	50,1	50,2	49,8
Breaking width, b (mm)	50,5	50,2	50,5	49,8	50,4	50,3	49,8	50,3	50,1	50,2
Span, l (mm)	250,0	250,0	250,0	250,0	250,0	250,0	250,0	250,0	250,0	250,0
Load increase (MPa/s)	0,25	0,25	0,25	0,25	0,25	0,25	0,25	0,25	0,25	0,25
Breaking load, F (N)	4380	3890	5010	4920	4220	3720	4170	4300	4640	4380
Distance fracture to centre (mm)	14,1	2,4	8,0	4,9	5,2	10,0	14,4	3,4	13,3	19,4
Flexural strength, R_{tf} (MPa)	12,9	11,7	15,0	14,7	12,7	11,0	12,4	12,8	13,8	13,2
Average flexural strength, \bar{R}_{tf}	13,0 MPa									
Standard deviation, s	1,2 MPa									
Lower expected value, E	10,6 MPa									

Remarks: The uncertainties are calculated and at the client's disposal

DISCLAIMER:

The laboratory is not responsible for the sampling or for the information declared by the client. The results refer only to the sample received at the laboratory, on the expressed date.
This report shall not be reproduced, except in full, without the written consent of the laboratory.

Digitally signed by

Antonio Molina
Director Técnico



Natural stone – Breaking load at dowel hole

REPORT Nº: **232936PN012A** DATE: **23-02-2023**

PAGE: **1/2**

PETITIONER: **LT Granit Oy**
Koskentie 4, FI-54410 Ylämaa. (Finland)

SAMPLE IDENTIFICATION:

Date of delivery **03-01-2023**
Description **10 slabs of nominal dimensions 200x200x30 mm**
Commercial name * **Baltic Brown**
Petrographic definition * **–**
Place of quarrying * **Helppääntie 422, FI-54410 Ylämaa, Finland**
Coordinates * **N: 60.833003, E: 27.846321**
Supplier * **LT Granit Oy**
Sampled by * **Jarmo Tielinen (05-10-2022)**
Planes of anisotropy * **–**

* Information declared by the petitioner

TEST METHOD: **EN 13364:2001 Natural stone test methods. Determination of the breaking load at dowel hole**

Deviations **–**
Specimen preparation **–**
Conditioning **Drying in oven at 70±5°C to constant mass**
Load direction **–**
Place of testing **Centro Tecnológico del Mármol**
Dates of testing **15-02-2023 / 20-02-2023**





TEST REPORT

Natural stone – Breaking load at dowel hole

REPORT Nº: **232936PN012A** DATE: **23-02-2023**

PAGE: **2/2**

RESULTS:

Specimen	59	60	61	62	63	64	65	66	67	68
Thickness, d (mm)	31	31	31	32	31	31	31	31	31	31
Breaking thickness, d_1 (mm)	11,4	9,8	11,8	11,1	11,7	10,9	11,0	11,5	10,9	11,0
Breaking load, F (N)	2400	1700	2450	2400	2500	2200	1950	2250	2550	2200
Maximum fracture length, b_A (mm)	32,8	44,3	46,8	60,6	42,0	37,3	35,0	41,8	45,7	31,0
Mean value of breaking load, \bar{F}	2250 N									
Standard deviation, s	250 N									
Lower expected value, E	1722 N									
Mean value of breaking thickness, \bar{d}_1	11,1 mm									
Mean value of maximum fracture lengths, \bar{b}_A	41,7 mm									

Remarks: The uncertainties are calculated and at the client's disposal
The results of breaking load and standard deviation are expressed to the nearest 50 N

DISCLAIMER:

The laboratory is not responsible for the sampling or for the information declared by the client. The results refer only to the sample received at the laboratory, on the expressed date.

This report shall not be reproduced, except in full, without the written consent of the laboratory.

Digitally signed by

Antonio Molina
Director Técnico



Natural stone – Slip resistance

REPORT Nº: **232936PN020A** DATE: **23-02-2023**

PAGE: **1/2**

PETITIONER: **LT Granit Oy**
Koskentie 4, FI-54410 Ylämaa. (Finland)


SAMPLE IDENTIFICATION:

Date of delivery **03-01-2023**
Description **3 slabs of 300x300x70 mm**
Surface finish * **Sawn**
Commercial name * **Baltic Brown**
Petrographic definition * **–**
Place of quarrying * **Helppääntie 422, FI-54410 Ylämaa, Finland**
Coordinates * **N: 60.833003, E: 27.846321**
Supplier * **LT Granit Oy**
Sampled by * **Jarmo Tielinen (05-10-2022)**

* Information declared by the petitioner

TEST METHOD: **EN 14231:2003 Natural stone test methods. Determination of the slip resistance by means of the pendulum tester**

Deviations **–**
Specimen preparation **–**
Slider used **76,2 x 25,4 mm**
Place of testing **Centro Tecnológico del Mármol**
Dates of testing **08-02-2023 / 09-02-2023**





TEST REPORT

Natural stone – Slip resistance

REPORT Nº: **232936PN020A** DATE: **23-02-2023**

PAGE: **2/2**

RESULTS:

Specimen	69.1	69.2	70.3	70.4	71.5	71.6
Individual values of the slip resistance, in dry condition	81	79	81	82	81	82
Individual values of the slip resistance, in wet condition	67	72	71	71	72	70
Average slip resistance, in dry condition (SRV "dry")	81		Uncertainty		± 1	
Average slip resistance, in wet condition (SRV "wet")	70		Uncertainty		± 2	

Remarks: The expanded uncertainty is based on a standard uncertainty multiplied by a coverage factor $K=2$, which for a normal distribution provides a level of confidence of about 95%

DISCLAIMER:

The laboratory is not responsible for the sampling or for the information declared by the client. The results refer only to the sample received at the laboratory, on the expressed date.

This report shall not be reproduced, except in full, without the written consent of the laboratory.

Digitally signed by

Antonio Molina
Director Técnico



Centro Tecnológico
del mármol

PN020JE2201

TEST REPORT

Slip resistance (slipperiness)

REPORT Nº: **232936PN020J** DATE: **23-02-2023**

PAGE: **1/2**

PETITIONER: **LT Granit Oy**
Koskentie 4, FI-54410 Ylämaa. (Finland)


SAMPLE IDENTIFICATION:

Date of delivery **03-01-2023**
Description **1 natural stone slab of 300x300x70 mm**
Surface finish * **Sawn**
Commercial name * **Baltic Brown**
Petrographic definition * **–**
Place of quarrying * **Helppääntie 422, FI-54410 Ylämaa, Finland**
Coordinates * **N: 60.833003, E: 27.846321**
Supplier * **LT Granit Oy**
Sampled by * **Jarmo Tielinen (05-10-2022)**

* Information declared by the petitioner

TEST METHOD: **EN 16165:2021 Determination of slip resistance of pedestrian surfaces - Methods of evaluation. Annex C Pendulum test**

Deviations **–**
Type of slider used **57**
Place of testing **Centro Tecnológico del Mármol**
Dates of testing **08-02-2023 / 09-02-2023**



Asociación Empresarial de Investigación Centro
Tecnológico del Mármol, la Piedra y Materiales
Ctra. de Murcia s/n. 30430 Cehegín, Murcia, Spain
Tel.: +34 968 741 500
<http://www.ctmarmol.es/>
email: laboratorio@ctmarmol.es



TEST REPORT

Slip resistance (slipperiness)

REPORT Nº: **232936PN020J** DATE: **23-02-2023**

PAGE: **2/2**

RESULTS:

Test conditions	Dry	Wet
Slipperiness measured towards 0°	81	66
Slipperiness measured towards 90°	78	69
Slipperiness measured towards 45°	82	71
Value of the slipperiness, <i>PTV</i>	78	66
Uncertainty	± 1	± 1

Remarks: The expanded uncertainty is based on a standard uncertainty multiplied by a coverage factor $K=2$, which for a normal distribution provides a level of confidence of about 95%

DISCLAIMER:

The laboratory is not responsible for the sampling or for the information declared by the client. The results refer only to the sample received at the laboratory, on the expressed date.

This report shall not be reproduced, except in full, without the written consent of the laboratory.

Digitally signed by

Antonio Molina
Director Técnico