



Centro Tecnológico
del mármol

PN003E2201

TEST REPORT

Natural stone – Water absorption

REPORT Nº: **232969PN003** DATE: **01-07-2023** PAGE: **1/2**

PETITIONER: **Tampereen Kovakivi Oy**
Poikeluksentie 192. 34300 Kuru. (Finland)

SAMPLE IDENTIFICATION:

Date of delivery **20-01-2023**
Description **6 cubic specimens of nominal dimensions 50x50x50 mm**
Commercial name * **Kivijärvi Black**
Petrographic definition * **Gabbro**
Place of quarrying * **Kivijärvi Quarry**
Supplier * **Tampereen Kovakivi Oy**
Sampled by * **Antti Elomaa (01-10-2022)**

* Information declared by the petitioner

TEST METHOD: **EN 13755:2008 Natural stone test methods. Determination of water absorption at atmospheric pressure**

Deviations –
Specimen preparation –
Place of testing **Centro Tecnológico del Mármol**
Dates of testing **24-05-2023 / 02-06-2023**



Asociación Empresarial de Investigación Centro
Tecnológico del Mármol, la Piedra y Materiales
Ctra. de Murcia s/n. 30430 Cehegín, Murcia, Spain
Tel.: +34 968 741 500
<http://www.ctmarmol.es/>
email: laboratorio@ctmarmol.es



TEST REPORT

Natural stone – Water absorption

REPORT Nº: 232969PN003

DATE: 01-07-2023

PAGE: 2/2

RESULTS:

Specimen

Water absorption, A_b (%)

Mean value of water absorption, \bar{A}_b

01	02	03	04	05	06
0,1	0,1	0,1	0,1	0,1	0,1
0,1 %					

Remarks: The uncertainties are calculated and at the client's disposal
The results are expressed to the nearest 0,1 %

DISCLAIMER:

The laboratory is not responsible for the sampling or for the information declared by the client. The results refer only to the sample received at the laboratory, on the expressed date.
This report shall not be reproduced, except in full, without the written consent of the laboratory.

Digitally signed by

Antonio Molina
Director Técnico



Natural stone – Apparent density and open porosity

REPORT Nº: **232969PN004A** DATE: **01-07-2023**

PAGE: **1/2**

PETITIONER: **Tampereen Kovakivi Oy**
Poikeluksentie 192. 34300 Kuru. (Finland)


SAMPLE IDENTIFICATION:

Date of delivery **20-01-2023**
Description **6 cubic specimens of nominal dimensions 50x50x50 mm**
Commercial name * **Kivijärvi Black**
Petrographic definition * **Gabbro**
Place of quarrying * **Kivijärvi Quarry**
Supplier * **Tampereen Kovakivi Oy**
Sampled by * **Antti Elomaa (01-10-2022)**

* Information declared by the petitioner

TEST METHOD: **EN 1936:2007 Natural stone test methods. Determination of real density and apparent density, and of total and open porosity. Section 8.1**

Deviations –
Specimen preparation –
Place of testing **Centro Tecnológico del Mármol**
Dates of testing **29-05-2023 / 01-06-2023**





TEST REPORT

Natural stone – Apparent density and open porosity

REPORT Nº: **232969PN004A** DATE: **01-07-2023**

PAGE: **2/2**

RESULTS:

Specimen

Apparent density, ρ_b (kg/m³)

Open porosity, p_o (%)

Mean value of apparent density, $\bar{\rho}_b$

Mean value of open porosity, \bar{p}_o

07	08	09	10	11	12
3000	3010	2980	3010	2980	2980
0,3	0,3	0,3	0,4	0,4	0,3
2990 kg/m ³					
0,3 %					

Remarks: The uncertainties are calculated and at the client's disposal
The results of density are expressed to the nearest 10 kg/m³
The results of porosity are expressed to the nearest 0,1 %

DISCLAIMER:

The laboratory is not responsible for the sampling or for the information declared by the client. The results refer only to the sample received at the laboratory, on the expressed date.
This report shall not be reproduced, except in full, without the written consent of the laboratory.

Digitally signed by

Antonio Molina
Director Técnico

Natural stone – Abrasion resistance (Capon method)

REPORT Nº: **232969PN006**

DATE: **01-07-2023**

PAGE: **1/2**

PETITIONER: **Tampereen Kovakivi Oy**
Poikeluksentie 192. 34300 Kuru. (Finland)


SAMPLE IDENTIFICATION:

Date of delivery **20-01-2023**
Description **6 polished slabs of 150x150x30 mm**
Commercial name * **Kivijärvi Black**
Petrographic definition * **Gabbro**
Place of quarrying * **Kivijärvi Quarry**
Supplier * **Tampereen Kovakivi Oy**
Sampled by * **Antti Elomaa (01-10-2022)**
Planes of anisotropy * **–**

* Information declared by the petitioner

TEST METHOD: **EN 14157:2017 Natural stone test methods. Determination of the abrasion resistance. Section 3**

Deviations **–**
Specimen preparation **–**
Calibration factor **0,1 mm**
Place of testing **Centro Tecnológico del Mármol**
Dates of testing **21-06-2023 / 23-06-2023**





TEST REPORT

Natural stone – Abrasion resistance (Capon method)

REPORT Nº: **232969PN006**

DATE: **01-07-2023**

PAGE: **2/2**

RESULTS:

Specimen	13	14	15	16	17	18
Groove lengths (mm)	16,0	15,5	15,0	15,5	15,0	15,0
	16,0	16,0	15,5	15,5	15,5	15,0
Mean value of groove length	15,5 mm					
Standard deviation	0,2 mm					
Higher expected value, E_H	16,0 mm					

Remarks:

The uncertainties are calculated and at the client's disposal
The results are expressed to the nearest 0,5 mm
According to EN 14157, only the biggest grooves of each specimen are considered

DISCLAIMER:

The laboratory is not responsible for the sampling or for the information declared by the client. The results refer only to the sample received at the laboratory, on the expressed date.
This report shall not be reproduced, except in full, without the written consent of the laboratory.

Digitally signed by

Antonio Molina
Director Técnico

Natural stone – Frost resistance (technological test)

REPORT Nº: **232969PN008B** DATE: **01-07-2023** PAGE: **1/4**PETITIONER: **Tampereen Kovakivi Oy**
Poikeluksentie 192. 34300 Kuru. (Finland)

SAMPLE IDENTIFICATION:

Date of delivery	20-01-2023
Description	2 sets of 10 specimens of nominal dimensions 300x50x50 mm
Commercial name *	Kivijärvi Black
Petrographic definition *	Gabbro
Place of quarrying *	Kivijärvi Quarry
Supplier *	Tampereen Kovakivi Oy
Sampled by *	Antti Elomaa (01-10-2022)
Planes of anisotropy *	–

* Information declared by the petitioner

TEST METHOD:	EN 12371:2010 Natural stone test methods. Determination of frost resistance. Section 7.3.1
Deviations	–
Specimen preparation	–
Conditioning	Drying in oven at 70±5°C to constant mass
Load direction	–
Place of testing	Centro Tecnológico del Mármol
Dates of testing	19-04-2023 / 26-06-2023



Natural stone – Frost resistance (technological test)

REPORT Nº: **232969PN008B** DATE: **01-07-2023**

PAGE: **2/4**

RESULTS:

Set 1 (not subjected to freeze-thaw cycles)

Specimen	49	50	51	52	53	54	55	56	57	58
Breaking thickness, h (mm)	49,7	50,2	49,5	50,4	50,6	50,5	50,5	50,6	50,6	50,6
Breaking width, b (mm)	50,4	52,4	50,3	52,8	50,2	49,9	52,0	53,5	52,4	51,2
Span, l (mm)	250,0	250,0	250,0	250,0	250,0	250,0	250,0	250,0	250,0	250,0
Load increase (MPa/s)	0,25	0,24	0,25	0,23	0,24	0,25	0,24	0,23	0,23	0,24
Breaking load, F (N)	7760	7930	8430	9090	8590	8760	8510	8670	8260	8420
Distance fracture to centre (mm)	1,1	7,3	16,2	4,4	3,8	4,4	2,9	13,8	4,4	2,8
Flexural strength, R_{tf} (MPa)	23,4	22,5	25,6	25,4	25,1	25,8	24,1	23,8	23,1	24,1

Set 2 (subjected to 56 freeze-thaw cycles)

Specimen	19	20	21	22	23	24	25	26	27	28
Breaking thickness, h (mm)	50,1	49,7	52,4	49,5	49,6	49,3	50,6	50,8	50,5	50,6
Breaking width, b (mm)	50,5	50,5	50,6	50,5	50,5	50,5	51,0	52,6	52,6	51,7
Span, l (mm)	250,0	250,0	250,0	250,0	250,0	250,0	250,0	250,0	250,0	250,0
Load increase (MPa/s)	0,25	0,25	0,22	0,25	0,25	0,25	0,24	0,23	0,23	0,24
Breaking load, F (N)	8800	8640	8380	8010	8260	8180	6330	8550	8140	8550
Distance fracture to centre (mm)	12,2	0,8	1,9	6,9	2,3	1,4	6,5	3,7	3,1	5,6
Flexural strength, R_{tf} (MPa)	26,1	26,0	22,6	24,3	25,0	25,0	18,2	23,6	22,8	24,2



TEST REPORT

Natural stone – Frost resistance (technological test)

REPORT Nº: **232969PN008B** DATE: **01-07-2023**

PAGE: **3/4**

Mean value of flexural strength, F_0

24,3 MPa

Standard deviation, s

1,1 MPa

Mean value of flexural strength after 56 cycles, F_{56}

23,8 MPa

Standard deviation, s

2,3 MPa

Decrease of flexural strength after 56 cycles

2,0 %

Remarks: The uncertainties are calculated and at the client's disposal

The sample received consisted of 20 undifferentiated specimens. The separation between the two sets of 10 specimens to be tested, was carried out at random by the laboratory

DISCLAIMER:

The laboratory is not responsible for the sampling or for the information declared by the client. The results refer only to the sample received at the laboratory, on the expressed date.

This report shall not be reproduced, except in full, without the written consent of the laboratory.

Digitally signed by


Antonio Molina
Director Técnico

Natural stone – Frost resistance (technological test)


REPORT Nº: 232969PN008B DATE: 01-07-2023

PAGE: 4/4

Set 2 before freeze-thaw cycles



Set 2 after 56 freeze-thaw cycles



Natural stone – Frost resistance (technological test)

REPORT Nº: **232969PN008D** DATE: **01-07-2023**

PAGE: **1/4**

PETITIONER: **Tampereen Kovakivi Oy**
Poikeluksentie 192. 34300 Kuru. (Finland)


SAMPLE IDENTIFICATION:

Date of delivery **20-01-2023, 02-03-2023**
Description **2 sets of 10 cubic specimens of nominal dimensions 70x70x70 mm**
Commercial name * **Kivijärvi Black**
Petrographic definition * **Gabbro**
Place of quarrying * **Kivijärvi Quarry**
Supplier * **Tampereen Kovakivi Oy**
Sampled by * **Antti Elomaa (01-10-2022)**
Planes of anisotropy * **–**

* Information declared by the petitioner

TEST METHOD: **EN 12371:2010 Natural stone test methods. Determination of frost resistance. Section 7.3.1**

Deviations **–**
Specimen preparation **–**
Conditioning **Drying in oven at 70±5°C to constant mass**
Load direction **–**
Place of testing **Centro Tecnológico del Mármol**
Dates of testing **19-04-2023 / 08-06-2023**



Natural stone – Frost resistance (technological test)

REPORT Nº: **232969PN008D** DATE: **01-07-2023**PAGE: **2/4**

RESULTS:

Set 1 (not subjected to freeze-thaw cycles)

Specimen	39	40	41	42	43	44	45	46	47	48
Average width of faces, \bar{l} (mm)	72,0	73,2	72,1	71,1	71,0	73,1	73,3	73,5	73,3	72,2
Height, h (mm)	71,6	70,0	71,4	74,0	74,2	70,0	70,0	70,2	70,4	71,3
Breaking load, F (kN)	1030	830	970	880	960	1060	1180	1090	930	1010
Compressive strength, R (MPa)	198	156	187	173	191	199	221	202	173	194

Set 2 (subjected to 56 freeze-thaw cycles)

Specimen	29	30	31	32	33	34	35	36	37	38
Average width of faces, \bar{l} (mm)	70,7	70,8	70,7	70,8	70,8	73,1	73,3	73,3	73,2	73,2
Height, h (mm)	73,9	73,8	74,1	74,6	73,9	70,2	70,4	70,0	70,1	70,3
Breaking load, F (kN)	1090	1090	1020	1040	1020	970	1120	1160	1010	1140
Compressive strength, R (MPa)	217	217	204	209	204	181	208	217	189	212



TEST REPORT

Natural stone – Frost resistance (technological test)

REPORT Nº: **232969PN008D** DATE: **01-07-2023**

PAGE: **3/4**

Mean value of compressive strength, R_0

189 MPa

Standard deviation, s

18 MPa

Mean value of compressive strength after 56 cycles, R_{56}

206 MPa

Standard deviation, s

12 MPa

Decrease of compressive strength after 56 cycles

0,0 %

Remarks: The uncertainties are calculated and at the client's disposal

The sample received consisted of 20 undifferentiated specimens. The separation between the two sets of 10 specimens to be tested, was carried out at random by the laboratory

DISCLAIMER:

The laboratory is not responsible for the sampling or for the information declared by the client. The results refer only to the sample received at the laboratory, on the expressed date.

This report shall not be reproduced, except in full, without the written consent of the laboratory.

Digitally signed by

Antonio Molina
Director Técnico

Natural stone – Frost resistance (technological test)

REPORT Nº: 232969PN008D DATE: 01-07-2023

PAGE: 4/4

Set 2 before freeze-thaw cycles



Set 2 after 56 freeze-thaw cycles



Natural stone – Compressive strength

REPORT Nº: **232969PN009A** DATE: **01-07-2023**

PAGE: **1/2**

PETITIONER: **Tampereen Kovakivi Oy**
Poikeluksentie 192. 34300 Kuru. (Finland)

SAMPLE IDENTIFICATION:

Date of delivery **20-01-2023, 02-03-2023**
Description **10 cubic specimens of nominal dimensions 70x70x70 mm**
Commercial name * **Kivijärvi Black**
Petrographic definition * **Gabbro**
Place of quarrying * **Kivijärvi Quarry**
Supplier * **Tampereen Kovakivi Oy**
Sampled by * **Antti Elomaa (01-10-2022)**
Planes of anisotropy * **–**

* Information declared by the petitioner

TEST METHOD: **EN 1926:2006 Natural stone test methods. Determination of uniaxial compressive strength**

Deviations **–**

Specimen preparation **–**

Conditioning **Drying in oven at 70±5°C to constant mass**

Load direction **–**

Place of testing **Centro Tecnológico del Mármol**

Dates of testing **05-06-2023 / 08-06-2023**



TEST REPORT

Natural stone – Compressive strength

REPORT Nº: **232969PN009A** DATE: **01-07-2023**

PAGE: **2/2**

RESULTS:

Specimen	39	40	41	42	43	44	45	46	47	48
Average width of faces, \bar{l} (mm)	72,0	73,2	72,1	71,1	71,0	73,1	73,3	73,5	73,3	72,2
Height, h (mm)	71,6	70,0	71,4	74,0	74,2	70,0	70,0	70,2	70,4	71,3
Breaking load, F (kN)	1030	830	970	880	960	1060	1180	1090	930	1010
Compressive strength, R (MPa)	198	156	187	173	191	199	221	202	173	194
Average compressive strength, \bar{R}	189 MPa									
Standard deviation, s	18 MPa									
Coefficient of variation, v	0,10									
Lower expected value, E	153 MPa									

Remarks: The uncertainties are calculated and at the client's disposal

DISCLAIMER:

The laboratory is not responsible for the sampling or for the information declared by the client. The results refer only to the sample received at the laboratory, on the expressed date.

This report shall not be reproduced, except in full, without the written consent of the laboratory.

Digitally signed by

Antonio Molina
Director Técnico



Natural stone – Flexural strength

REPORT Nº: **232969PN010** DATE: **01-07-2023** PAGE: **1/2**

PETITIONER: **Tampereen Kovakivi Oy**
Poikeluksentie 192. 34300 Kuru. (Finland)

SAMPLE IDENTIFICATION:

Date of delivery **20-01-2023**
Description **10 specimens of nominal dimensions 300x50x50 mm**
Commercial name * **Kivijärvi Black**
Petrographic definition * **Gabbro**
Place of quarrying * **Kivijärvi Quarry**
Supplier * **Tampereen Kovakivi Oy**
Sampled by * **Antti Elomaa (01-10-2022)**
Planes of anisotropy * **–**

* Information declared by the petitioner

TEST METHOD: **EN 12372:2022 Natural stone test methods. Determination of flexural strength under concentrated load**

Deviations **–**
Specimen preparation **–**
Conditioning **Drying in oven at 70±5°C to constant mass**
Load direction **–**
Place of testing **Centro Tecnológico del Mármol**
Dates of testing **21-06-2023 / 26-06-2023**





TEST REPORT

Natural stone – Flexural strength

REPORT Nº: 232969PN010

DATE: 01-07-2023

PAGE: 2/2

RESULTS:

Specimen	49	50	51	52	53	54	55	56	57	58
Breaking thickness, h (mm)	49,7	50,2	49,5	50,4	50,6	50,5	50,5	50,6	50,6	50,6
Breaking width, b (mm)	50,4	52,4	50,3	52,8	50,2	49,9	52,0	53,5	52,4	51,2
Span, l (mm)	250,0	250,0	250,0	250,0	250,0	250,0	250,0	250,0	250,0	250,0
Load increase (MPa/s)	0,25	0,24	0,25	0,23	0,24	0,25	0,24	0,23	0,23	0,24
Breaking load, F (N)	7760	7930	8430	9090	8590	8760	8510	8670	8260	8420
Distance fracture to centre (mm)	1,1	7,3	16,2	4,4	3,8	4,4	2,9	13,8	4,4	2,8
Flexural strength, R_{tf} (MPa)	23,4	22,5	25,6	25,4	25,1	25,8	24,1	23,8	23,1	24,1
Average flexural strength, \bar{R}_{tf}	24,3 MPa									
Standard deviation, s	1,1 MPa									
Lower expected value, E	22,0 MPa									

Remarks: The uncertainties are calculated and at the client's disposal

DISCLAIMER:

The laboratory is not responsible for the sampling or for the information declared by the client. The results refer only to the sample received at the laboratory, on the expressed date.
This report shall not be reproduced, except in full, without the written consent of the laboratory.

Digitally signed by

Antonio Molina
Director Técnico

Natural stone – Breaking load at dowel hole

REPORT Nº: **232969PN012A** DATE: **01-07-2023**

PAGE: **1/2**

PETITIONER: **Tampereen Kovakivi Oy**
Poikeluksentie 192. 34300 Kuru. (Finland)

SAMPLE IDENTIFICATION:

Date of delivery **20-01-2023**
Description **10 slabs of nominal dimensions 200x200x30 mm**
Commercial name * **Kivijärvi Black**
Petrographic definition * **Gabbro**
Place of quarrying * **Kivijärvi Quarry**
Supplier * **Tampereen Kovakivi Oy**
Sampled by * **Antti Elomaa (01-10-2022)**
Planes of anisotropy * **–**

* Information declared by the petitioner

TEST METHOD: **EN 13364:2001 Natural stone test methods. Determination of the breaking load at dowel hole**

Deviations **–**
Specimen preparation **–**
Conditioning **Drying in oven at 70±5°C to constant mass**
Load direction **–**
Place of testing **Centro Tecnológico del Mármol**
Dates of testing **14-06-2023 / 19-06-2023**





TEST REPORT

Natural stone – Breaking load at dowel hole

REPORT Nº: **232969PN012A** DATE: **01-07-2023**

PAGE: **2/2**

RESULTS:

Specimen	59	60	61	62	63	64	65	66	67	68
Thickness, d (mm)	30	29	30	30	30	30	30	30	29	30
Breaking thickness, d_1 (mm)	10,6	10,8	10,8	10,3	11,0	10,6	10,6	10,2	11,0	10,7
Breaking load, F (N)	4400	2900	3750	4150	3900	3750	3500	3750	3800	3650
Maximum fracture length, b_A (mm)	41,4	31,6	41,0	42,6	42,9	43,1	42,9	42,9	34,7	32,0
Mean value of breaking load, \bar{F}	3750 N									
Standard deviation, s	400 N									
Lower expected value, E	2969 N									
Mean value of breaking thickness, \bar{d}_1	10,7 mm									
Mean value of maximum fracture lengths, \bar{b}_A	39,5 mm									

Remarks: The uncertainties are calculated and at the client's disposal
The results of breaking load and standard deviation are expressed to the nearest 50 N

DISCLAIMER:

The laboratory is not responsible for the sampling or for the information declared by the client. The results refer only to the sample received at the laboratory, on the expressed date.

This report shall not be reproduced, except in full, without the written consent of the laboratory.

Digitally signed by

Antonio Molina
Director Técnico



TEST REPORT

Natural stone – Slip resistance

REPORT Nº: **232969PN020A** DATE: **05-07-2023**

PAGE: **1/2**

PETITIONER: **Tampereen Kovakivi Oy**
Poikeluksentie 192. 34300 Kuru. (Finland)

SAMPLE IDENTIFICATION:

Date of delivery **20-01-2023**
Description **3 slabs of 300x300x50 mm**
Surface finish * **Sawn**
Commercial name * **Kivijärvi Black**
Petrographic definition * **Gabbro**
Place of quarrying * **Kivijärvi Quarry**
Supplier * **Tampereen Kovakivi Oy**
Sampled by * **Antti Elomaa (01-10-2022)**

* Information declared by the petitioner

TEST METHOD: **EN 14231:2003 Natural stone test methods. Determination of the slip resistance by means of the pendulum tester**

Deviations **–**
Specimen preparation **–**
Slider used **76,2 x 25,4 mm**
Place of testing **Centro Tecnológico del Mármol**
Dates of testing **05-07-2023**





TEST REPORT

Natural stone – Slip resistance

REPORT Nº: **232969PN020A** DATE: **05-07-2023**

PAGE: **2/2**

RESULTS:

Specimen	69.1	69.2	70.3	70.4	71.5	71.6
Individual values of the slip resistance, in dry condition	69	70	64	64	64	66
Individual values of the slip resistance, in wet condition	40	38	41	43	40	41
Average slip resistance, in dry condition (SRV “dry”)	66		Uncertainty		± 3	
Average slip resistance, in wet condition (SRV “wet”)	41		Uncertainty		± 2	

Remarks: The expanded uncertainty is based on a standard uncertainty multiplied by a coverage factor $K=2$, which for a normal distribution provides a level of confidence of about 95%

DISCLAIMER:

The laboratory is not responsible for the sampling or for the information declared by the client. The results refer only to the sample received at the laboratory, on the expressed date.

This report shall not be reproduced, except in full, without the written consent of the laboratory.

Digitally signed by

Antonio Molina
Director Técnico



TEST REPORT

Slip resistance (slipperiness)

REPORT Nº: **232969PN020J** DATE: **05-07-2023** PAGE: **1/2**

PETITIONER: **Tampereen Kovakivi Oy**
Poikeluksentie 192. 34300 Kuru. (Finland)


SAMPLE IDENTIFICATION:

Date of delivery **20-01-2023**
Description **1 natural stone slab of 300x300x50 mm**
Surface finish * **Sawn**
Commercial name * **Kivijärvi Black**
Petrographic definition * **Gabbro**
Place of quarrying * **Kivijärvi Quarry**
Supplier * **Tampereen Kovakivi Oy**
Sampled by * **Antti Elomaa (01-10-2022)**

* Information declared by the petitioner

TEST METHOD: **EN 16165:2021 Determination of slip resistance of pedestrian surfaces - Methods of evaluation. Annex C Pendulum test**

Deviations **–**
Type of slider used **57**
Place of testing **Centro Tecnológico del Mármol**
Dates of testing **05-07-2023**





TEST REPORT

Slip resistance (slipperiness)

REPORT Nº: **232969PN020J** DATE: **05-07-2023**

PAGE: **2/2**

RESULTS:

Test conditions	Dry	Wet
Slipperiness measured towards 0°	67	40
Slipperiness measured towards 90°	70	35
Slipperiness measured towards 45°	70	37
Value of the slipperiness, <i>PTV</i>	67	35
Uncertainty	± 3	± 3

Remarks: The expanded uncertainty is based on a standard uncertainty multiplied by a coverage factor $K=2$, which for a normal distribution provides a level of confidence of about 95%

DISCLAIMER:

The laboratory is not responsible for the sampling or for the information declared by the client. The results refer only to the sample received at the laboratory, on the expressed date.

This report shall not be reproduced, except in full, without the written consent of the laboratory.

Digitally signed by

Antonio Molina
Director Técnico